

# MetsäBoard Classic FBB CX

## PRODUCT SHEET

### PRODUCT DESCRIPTION

Fully coated paperboard, no OBA in top coating


### MAIN END USES

Cigarettes

### FEATURES

Printing methods Gravure, Offset, Flexo  
Mill Metsä Board Tako, Metsä Board Äänekoski

### STRUCTURE



- 1) Multiple blade coating
- 2) Bleached chemical pulp
- 3) Chemi-thermo-mechanical pulp (CTMP)
- 4) Bleached chemical pulp

## TECHNICAL INFORMATION

PROPERTY, UNIT	METHOD	STANDARD	TOLERANCE			VALUES
Grammage g/m <sup>2</sup>		ISO 536	± 4%	200	215	225
Thickness µm		ISO 534	± 4%	305	330	350

Tolerances, when specified, are based on 95% confidence limits on mill measurements of samples tested in paperboard manufacturing conditions.  
No added optical brightening agents (OBA). Metsä Board Paperboard mills have PEFC(TM) and FSC® chain of custody certificates.  
Issued 02.07.2020. Supersedes sheet dated 06.11.2017