

# MetsäBoard Natural FBB NEW

## PRODUCT SHEET

### PRODUCT DESCRIPTION

Folding boxboard, uncoated, hard sized, OBA free


### MAIN END USES

Beautycare, Healthcare, Foods, Beverages, Frozen food, Paper plates, Folded trays, Fast food applications

### FEATURES

Printing methods      Offset, Flexo  
 Food contact          EU Regulation (EC) No 1935/2004, GB9685, GB4806.8, USFDA21CFR§176.170\*, USFDA21CFR§176.180\*  
 Mill                      Metsä Board Husum

### STRUCTURE



- 1) Bleached chemical pulp
- 2) Bleached chemi-thermo-mechanical pulp (BCTMP)
- 3) Bleached chemical pulp

## TECHNICAL INFORMATION

PROPERTY, UNIT	METHOD	STANDARD	TOLERANCE	VALUES										
Grammage g/m <sup>2</sup>		ISO 536	±2%	175	190	200	210	225	235	245	260	270	295	325
Bending stiffness CD mNm	Taber 15°	ISO 2493	± 15%	4.0	4.8	5.7	6.8	8.3	9.2	10.2	11.8	13.2	16.2	19.2
Bending stiffness MD mNm	Taber 15°	ISO 2493	± 15%	8.0	9.9	11.3	13.7	16.7	18.6	20.4	23.5	26.5	32.7	38.2
Thickness µm		ISO 534	± 3%	310	335	360	385	415	435	455	485	505	555	610
Moisture content %		ISO 287	± 1.0	7.0	7.0	7.0	7.2	7.5	7.7	7.7	7.8	8.1	8.3	8.5
Brightness top %	Illumination C/2°	ISO 2470-1	± 1	80.5	80.5	80.5	80.5	80.5	80.5	80.5	80.5	80.5	80.5	80.5
Water absorption top g/m <sup>2</sup>	Cobb 3 min	ISO 535		≤40	≤40	≤40	≤40	≤40	≤40	≤40	≤40	≤40	≤40	≤40
Water absorption middle, back g/m <sup>2</sup>	Cobb 3 min	ISO 535		≤50	≤50	≤50	≤50	≤50	≤50	≤50	≤50	≤50	≤50	≤50
Off-flavour (Robinson test)	12 months in original package	EN 1230-2		<1	<1	<1	<1	<1	<1	<1	<1	<1	<1	<1

Tolerances, when specified, are based on 95% confidence limits on single mill measurements of random samples measured in manufacturing conditions.

Metsä Board Paperboard mills have PEFC chain of custody, FSC chain of custody and FSC controlled wood certificates.

\*Please contact Metsä Board for details of country-specific restrictions and/or limitations.

Issued 24.04.2019. Supersedes sheet dated 04.05.2017