

MetsäBoard Prime FBB CX

PRODUCT SHEET

PRODUCT DESCRIPTION

Fully coated paperboard with coated back, top and back coating contains OBA


MAIN END USES

Cigarettes

FEATURES

Printing methods Gravure, Offset, Flexo
Mill Metsä Board Tako, Metsä Board Äänekoski

STRUCTURE



- 1) Multiple blade coating
- 2) Bleached chemical pulp
- 3) Chemi-thermo-mechanical pulp (CTMP)
- 4) Bleached chemical pulp
- 5) Light weight coating

TECHNICAL INFORMATION

PROPERTY, UNIT	METHOD	STANDARD	TOLERANCE	VALUES
Grammage g/m ²		ISO 536	± 4%	215
Thickness µm		ISO 534	± 4%	315

Tolerances, when specified, are based on 95% confidence limits on mill measurements of samples tested in paperboard manufacturing conditions.
Metsä Board Paperboard mills have PEFC(TM) and FSC® chain of custody certificates.
Issued 28.10.2020. Supersedes sheet dated 02.07.2020